

## Aluminium

## 2014A T6511 Bar & Extrusion

Datasheet Updated  
05 August 2021

### RANGE

Product Form	Imperial Sizes	Metric Sizes
Round Bar	3/16" - 16"	6.0mm - 50.0mm

### SPECIFICATIONS

Commercial	2014A T6511
EN	2014A T6511

A high strength aluminium alloy which retains its strength after heat treatment.

### CHEMICAL COMPOSITION

BS EN 573-3  
Alloy 2014

Element	% Present
Silicon (Si)	0.50 - 0.90
Iron (Fe)	0.50 max
Copper (Cu)	3.90 - 5.00
Zinc (Zn)	0.25 max
Manganese (Mn)	0.40 - 1.20
Magnesium (Mg)	0.20 - 0.80
Titanium (Ti)	0.15 max
Others (Total)	0.15 max
Chromium (Cr)	0.10 max
Nickel (Ni)	0.10 max
Other (Each)	0.05 max
Titanium + Zirconium (Ti+Zr)	0.20 max
Aluminium (Al)	Balance

### TEMPER TYPES

This datasheet relates to temper T6511. The most common tempers for aluminium alloy 2014A are:

- T3
- T6511
- T651
- T6

### SUPPLIED FORMS

- Bar
- Extrusions

### APPLICATIONS

- High strength aerospace components
- Military vehicles
- Bridges
- Weapons manufacture
- Structural applications

### CHARACTERISTICS

- Machinability of aluminium alloy 2014A is very good.
- Resistance to atmospheric attack is poor especially when exposed to water or salt environments. To protect against atmospheric corrosion in storage, lightly coat with lanolin based protective oil.
- Good hard anodising capability
- Good strength levels after heat treatment

## MECHANICAL PROPERTIES

### BS EN 755-2

#### Profile 25mm to 75mm Wall Thickness

Property	Value
Proof Stress	415 Min MPa
Tensile Strength	460 Min MPa
Hardness Brinell	140 HB
Elongation A	7 Min %

### BS EN 755-2

#### Profile Up to 25mm Wall Thickness

Property	Value
Proof Stress	370 Min MPa
Tensile Strength	415 Min MPa
Elongation A50 mm	5 Min %
Hardness Brinell	140 HB
Elongation A	7 Min %

### BS EN 755-2

#### Tube 10mm to 40mm Wall Thickness

Property	Value
Proof Stress	400 Min MPa
Tensile Strength	450 Min MPa
Elongation A50 mm	4 Min %
Hardness Brinell	140 HB
Elongation A	6 Min %

### BS EN 755-2

#### Tube Up to 10mm Wall Thickness

Property	Value
Proof Stress	370 Min MPa
Tensile Strength	415 Min MPa
Hardness Brinell	140 HB
Elongation A	7 Min %
Elongation A50 mm	5 Min %

### BS EN 755-2

#### Bar 150mm to 200mm Dia. & A/F

Property	Value
Proof Stress	350 Min MPa
Tensile Strength	430 Min MPa
Hardness Brinell	140 HB
Elongation A	6 Min %

### BS EN 755-2

#### Bar 75mm to 150mm Dia. & A/F

Property	Value
Proof Stress	420 Min MPa
Tensile Strength	465 Min MPa
Hardness Brinell	140 HB
Elongation A	7 Min %

### BS EN 755-2

#### Bar 25mm to 75mm Dia. & A/F

Property	Value
Proof Stress	415 Min MPa
Tensile Strength	460 Min MPa
Hardness Brinell	140 HB
Elongation A	7 Min %

### BS EN 755-2

#### Rod & Bar Up to 25mm Dia. & A/F

Property	Value
Tensile Strength	415 Min MPa
Proof Stress	370 Min MPa
Hardness Brinell	140 HB
Elongation A50 mm	5 Min %
Elongation A	6 Min %

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.