

Aluminium

5754 H111 Sheet & Plate

Datasheet Updated

11 January 2024

SPECIFICATIONS

Commercial	5754 H111
EN	5754 H111

Superb corrosion resistance and ideal for use in marine, nuclear, chemical or oil & gas industries.

CHEMICAL COMPOSITION

BS EN 573-3

Alloy 5754

Element	% Present
Manganese (Mn)	0.00 - 0.50
Iron (Fe)	0.00 - 0.40
Magnesium (Mg)	2.60 - 3.60
Silicon (Si)	0.00 - 0.40
Chromium (Cr)	0.00 - 0.30
Copper (Cu)	0.00 - 0.10
Manganese + Chromium (Mn+Cr)	0.10 - 0.60
Other (Each)	0.00 - 0.05
Others (Total)	0.00 - 0.15
Titanium (Ti)	0.00 - 0.15
Zinc (Zn)	0.00 - 0.20
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Alloy 5754 also corresponds to the following standard designations and specifications *but may not be a direct equivalent*:

- A95754
- Al Mg3
- Al 3.1Mg Mn Cr
- AW-5754

TEMPER TYPES

The most common tempers for 5754 aluminium are shown below with H114 & H111 being the most common treadplate temper

- H114
- H22
- H24
- H26
- O
- H111

SUPPLIED FORMS

- Treadplate/Patterned Sheet
- Sheet
- Plate

APPLICATIONS

- Treadplate
- Shipbuilding
- Vehicle bodies
- Rivets
- Fishing industry equipment
- Food processing
- Welded chemical and nuclear structures

CHARACTERISTICS

- Excellent weldability
- Good formability
- Excellent resistance to seawater & industrial chemical corrosion



MECHANICAL PROPERTIES

BS EN 485-2

Sheet 0.2mm to 6.00mm

Property	Value
Proof Stress	60 Min MPa
Tensile Strength	160 - 200 MPa
Hardness Brinell	44 HB
Elongation A50 mm	12 Min %

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.