

Aluminium

QQ-A-200/3 T3 Bar & Extrusion

Datasheet Updated
05 August 2021

SPECIFICATIONS

Commercial	2024
Aerospace	QQ-A-200/3 T3

A high strength aerospace aluminium alloy.

CHEMICAL COMPOSITION

SAE AMS QQ-A-200/3
Alloy QQ-A-200/3

Element	% Present
Silicon (Si)	0.00 - 0.50
Iron (Fe)	0.00 - 0.50
Copper (Cu)	3.80 - 4.90
Manganese (Mn)	0.30 - 0.90
Chromium (Cr)	0.00 - 0.10
Magnesium (Mg)	1.20 - 1.80
Zinc (Zn)	0.00 - 0.25
Titanium (Ti)	0.00 - 0.15
Other (Each)	0.00 - 0.05
Others (Total)	0.00 - 0.15
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Aluminium alloy QQ-A-200/3 has similarities to the following standard designations and specifications:

- AMS 4164
- AMS 4165

TEMPER TYPES

Alloy QQ-A-200/3 is supplied in a range of tempers:

- T3
- T3511
- T8511

SUPPLIED FORMS

- Bar
- Extrusions

APPLICATIONS

Commonly used in:

- Aircraft structural components
- Truck wheels
- Medical instruments
- Screw machine products

CHARACTERISTICS

- High strength
- Very good machinability
- Very good weldability
- Improved stress corrosion cracking resistance
- Excellent fatigue resistance

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

