

Copper Alloys

CW712R (CZ112) Bar

Datasheet Updated
05 August 2021

RANGE

Product Form	Size Range
Round Bar EN12163	3/16"- 4"

SPECIFICATIONS

Commercial	CZ112
EN	CW712R

Brass alloy with the addition of tin, used in a wide range of marine and subsea applications.

CHEMICAL COMPOSITION

EN 12163
CW712R Brass Rod

Element	% Present
Copper (Cu)	61.00 - 63.00
Tin (Sn)	1.00 - 1.50
Lead (Pb)	0.20 - 0.60
Iron (Fe)	0.00 - 0.10
Nickel (Ni)	0.00 - 0.20
Others (Total)	0.00 - 0.20
Zinc (Zn)	Balance

ALLOY DESIGNATIONS

CZ112/CW712R corresponds to the following designation **but may not be a direct equivalent**:

- CuZn36Sn1Pb

SUPPLIED FORMS

- Bar

APPLICATIONS

- Heat exchanger tubeplates
- Marine components
- Fasteners in corrosion resistant applications
- High strength cold headed products
- Hardware for subsea applications
- General machined components

CHARACTERISTICS

- Very good corrosion resistance in marine environments
- Excellent hot formability
- Good strength
- Retention of properties at cryogenic temperatures

MECHANICAL PROPERTIES

EN 12163
Bar From 5mm to 60mm Dia.

Property	Value
Proof Stress	160-200 MPa
Tensile Strength	340-400 MPa
Hardness Brinell	80 - 135 HB
Elongation A	25 - 20 %

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.