







Nickel Alloys

Alloy 625 Bar & Forgings

Datasheet Updated 05 August 2021

SPECIFICATIONS

Commercial

Alloy 625

A nickel-chromium-molybdenum-niobium alloy with excellent resistance to a variety of corrosive media.

CHEMICAL COMPOSITION

ASTM B446-03 Alloy 625

Element	% Present
Nickel (Ni)	58.00 - 0.00
Chromium (Cr)	20.00 - 23.00
Molybdenum (Mo)	8.00 - 10.00
Aluminium (AI)	0.00 - 0.40
Carbon (C)	0.00 - 0.10
Cobalt (Co)	0.00 - 1.00
Columbium + Tantalum (Cb+Ta)	3.15 - 4.15
Iron (Fe)	0.00 - 5.00
Manganese (Mn)	0.00 - 0.50
Phosphorous (P)	0.00 - 0.02
Silicon (Si)	0.00 - 0.50
Sulphur (S)	0.00 - 0.02
Titanium (Ti)	0.00 - 0.40

ALLOY DESIGNATIONS

- ASTM B446-03 (2014) UNS N06625
- NACE MR0175/ISO 15156-3

SUPPLIED FORMS

- Bar
- Forgings
- Rod

APPLICATIONS

- Equipment for production of phosphoric acid
- Radioactive waste treatment plants
- Oil production pipe systems and riser linings
- Offshore industry and seawater exposed equipment
- Sea-water piping in shipbuilding
- Stress corrosion cracking resistant compensators
- Furnace linings
- Components in oil and gas extraction
- Fasteners
- Wellhead components
- Propellers and shafts

CHARACTERISTICS

- Exceptional resistance to pitting, crevice corrosion, erosion and intergranular corosion
- Immunity to chloride-induced stress corrosion cracking
- Good resistance to mineral acids such as nitric, phosphoric, sulfuric, and hydrochloric acids
- Good resistance to alkalis and organic acids
- Good mechanical properties
- Excellent weldability
- Low magnetic permeability
- Non magnetic and spark resistant









MECHANICAL PROPERTIES

ASTM B446-03 UNS N06625 Grade 1 Hot Worked Rod & Bar, Annealed Up to 4in (102mm) incl.

Property	Value
Proof Stress	415 Min MPa
Tensile Strength	830 Min MPa
Elongation A50 mm	30 Min %

ASTM B446-03UNS N06625 Grade 1 Hot Worked Rod & Bar, Annealed Over 4in (102mm) -10 in (254mm)

Property	Value
Proof Stress	345 Min MPa
Tensile Strength	760 Min MPa
Elongation A50 mm	25 Min %

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed S online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.