

Stainless Steel

AMS 5659 (15-5) Bar

Datasheet Updated
05 August 2021

SPECIFICATIONS

Commercial	15-5
Aerospace	AMS 5659

A martensitic precipitation hardening chromium-nickel-copper stainless steel.

CHEMICAL COMPOSITION

AMS 5659

Element	% Present
Carbon (C)	0.00 - 0.07
Chromium (Cr)	14.00 - 15.50
Manganese (Mn)	0.00 - 1.00
Silicon (Si)	0.00 - 1.00
Phosphorous (P)	0.00 - 0.03
Sulphur (S)	0.00 - 0.02
Nickel (Ni)	3.50 - 5.50
Copper (Cu)	2.50 - 4.50
Molybdenum (Mo)	0.00 - 0.50
Niobium (Columbium) (Nb)	0.00 - 0.45
Iron (Fe)	Balance

ALLOY DESIGNATIONS

- 15/5 PH
- UNS S15500
- AMS 5659

SUPPLIED FORMS

This is a bar specification, typically available in round and hexagon.

- Bar

APPLICATIONS

- Aircraft components
- Cylinders
- Engine parts
- Fittings
- Gears
- Hollow shafts
- Marine gas turbine compressor sections
- Paper mill equipment
- Shafts
- Valves

CHARACTERISTICS

- High strength
- Excellent corrosion resistance
- Good mechanical properties
- Superior toughness than 17-4

MECHANICAL PROPERTIES

AMS 5659

Property	Value
Proof Stress	700-1170 MPa
Tensile Strength	930-1310 MPa
Elongation A50 mm	10-16 %
Hardness Brinell	277-444 HB

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon. Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources. Material supplied by the Company may vary significantly from this data but will conform to all relevant and applicable standards. As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied. Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.